

# NICKEL PELLETS

**CHEMICAL COMPOSITIONS, %**  
(as per manufacturer's technical conditions)

Grade	<b>DNK 0</b>	DNK 1
Ni min	99.95	99.92
C max	0.015	0.05
Fe max	0.015	0.03
S max	0.001	0.0015
Si max	0.001	0.001
Cu max	0.001	0.001
Al max	0.001	0.001
Co max	0.0005	0.0005
Mg max	0.0005	0.0005
P max	0.0005	0.0005
Zn max	0.0005	0.0005
As max	0.0005	0.0005
Te max	0.0005	0.0005
Tl max	0.0005	0.0005
Mn max	0.0005	0.0005
Pb max	0.0001	0.0001
Cd max	0.0001	0.0001
Ag max	0.0001	0.0001
Bi max	0.0001	0.0001
Sn max	0.0001	0.0001
Sb max	0.0001	0.0001

## DIMENSIONS

Nickel pellets should have a nearly spherical form with 7-10 mm in diameter. Pellets of other size are allowed, but not more than 10% of the batch. Non-spherical form units are allowed, but not more than 3% of the batch.



## PACKING

In steel drums, net weight of each drum up to 250 kgs, four drums on pallet.

